ABSTRACT OF THE DISCLOSURE

5   The present invention relates to compositions of matter represented by the general formula

$$Ln_xLn'_{x'}A_yTi_zCe_{1-x-x'-y-z}O_{2-\delta}$$

10   wherein Ln is selected from the group consisting of Sm, Gd, Y, and mixtures thereof; Ln' is selected from the group consisting of La, Pr, Nd, Pm, Eu, Tb, Dy, Ho, Er, Tm, Yb, Lu, A is selected from the group consisting of Mg, Ca, Sr and Ba, $0.05 \leq x \leq 0.25$, $0 \leq x' \leq 0.25$, $0 \leq y \leq 0.03$, $0.001 \leq z \leq 0.03$, $0.05 \leq x + x' \leq 0.25$, $0.001 \leq y + z \leq 0.03$, wherein δ is a number which renders the composition of matter charge neutral. The

15   compositions can be formed into sintered bodies suitable for use as solid electrolytes in devices including solid-state oxygen generators. Such sintered bodies have greater than 95% theoretical density at temperatures at or below 1600°C, and can be produced by a solid-state method.